



ARDEX A 46

External Patching Compound

Easy to install

External repairs to concrete floors

Rapid hardening - walkable after 2 - 3 hours

ARDEX Australia Pty Ltd
2 Buda Way
Kemps Creek NSW 2178
1300 788 780
technicalservices@ardexaustralia.com
ardexaustralia.com

ARDEX New Zealand Ltd
15 Alfred Street
Onehunga, Auckland, 1061
Phone: 0800 227 339
Email: info@ardexnz.com
ardex.co.nz

ARDEX A 46

External Patching Compound

DESCRIPTION

ARDEX A 46 is a rapid hardening, rapid drying, slump-free mortar for external repairs. It is ideal for repairing and resurfacing concrete stair treads and risers and concrete subfloors. Also for filling and patching cracks in walls, ceilings, window and door frames, and can be used to form ramps from 2mm – 30mm. Mix mortar sets 15 - 20 minutes and can normally be walked on after approximately 2-3 hours at 23°C.

SURFACE PREPARATION

ARDEX A46 can be applied directly to dry or moist substrates provided they are set and hardened and the surface is sound, free of dust, grease, oil and other surface contamination. Worn or trafficked surfaces should be abraded with a diamond grinder or scarifier to remove any contamination and to roughen concrete to expose a clean porous surface to ensure good adhesion. Subfloor temperatures must be a minimum of 10°C, and maximum of 35°C. For further information, contact ARDEX technical services.

MIXING RATIO

Approximately 4.8 - 5.6 litres of water to 20 kg of ARDEX A 46 powder, or; 1 volume of water to 3.5 volumes of ARDEX A 46 powder.

MIXING

ARDEX repair products react and harden quickly when mixed with water. Thorough mixing in the shortest possible time is essential to ensure a lump free, slump resistant mortar. Always mix the powder into the water.

The most efficient method of mixing is by using an ARDEX mixing paddle and a heavy duty electric drill (650 rpm). To 4.8 - 5.6 litres of water, add the ARDEX A 46 (20 kg) whilst mixing thoroughly. Do not overwater. If the mix initially appears dry, continue mixing for a full 2 - 3 minutes until a creamy non-slump mortar is achieved, do not add additional water. The mixed mortar has a working time of 15 - 20 minutes at 23°C. This time will be extended in cooler temperatures, and reduced at higher temperatures.

THICKNESS

ARDEX A 46 can be applied from 2 – 30mm in one application.

INSTALLATION

For repairs, apply the mortar with a trowel to holes, cracks and damaged areas, ensuring that the mortar “wets” the surface by trowelling in firmly, leaving the repair proud. After approximately 15 minutes, trim off excess and finish off with a wet trowel, sponge, or sponge float to obtain a smooth surface. For ramps, work the mortar into the prepared substrates with a trowel. If floorcoverings are to be installed, ARDEX A 46 must be left for 24 hours. If the product is to be coated, it should be left for 2 days up to 5mm, 5 days up to 10mm, 7 days up to 20mm and 10 days up to 30 mm. These times will be shorter in warm conditions and longer in cool conditions.

Note: Exterior installations must be protected from direct sunlight and draughts which could lead to accelerated drying of the surface.

LIMITATIONS

ARDEX A 46 is suitable for foot traffic and light duty, soft wheeled, vehicle traffic. Do not use for heavy duty areas such as areas subjected to heavy vehicles, or heavily trafficked areas.

COVERAGE

Approximately 1.4kg powder/mm/m². A 20kg bag will cover approximately 5.5m² at 2mm thickness

PACKAGING

ARDEX A 46 is packed in polylined paper sacks – net weight 20kg.

SHELF LIFE

ARDEX A 46 has a shelf life of 12 months if stored in dry conditions, in unopened packaging at 23°C and 50% relative humidity.

SAFETY DATA

This product causes skin irritation and may cause an skin allergic reaction. It may cause respiratory irritation and it causes serious eye damage. This product may cause cancer and it causes damage to organs through prolonged or repeated exposure. In case of contact with the eyes rinse with running water until advised to stop by the Poisons Information Centre or a doctor, or for at least 15 minutes. Wear protective gloves, clothing, eye, and face protection. Avoid inhaling dust/fumes. Ensure adequate ventilation during mixing and application. Store locked up. Check with your local Council regarding the disposal of contents, dispose of packaging thoughtfully. Keep out of the reach of children. Call

ARDEX A 46

External Patching Compound

the Poisons Information Centre on 131 126 (AUS) and 0800 764 766 (NZ) or call a doctor if you feel unwell. Additional information is in the Safety Data Sheet (SDS) at ardexaustralia.com

TECHNICAL DATA	
Bulk density of powder	1.3 g/L
Weight of fresh mortar	1.8 g/L
COMPRESSIVE STRENGTH	
After 1 day	10 MPa
After 7 days	20 MPa
After 28 days	25 MPa
FLEXURAL STRENGTH	
After 1 day	2 MPa
After 7 days	4 MPa
After 28 days	6 MPa

GUARANTEE

Ardex Australia Pty Ltd (“we” or “us”) guarantees this product (“our goods”) is free from manufacturing defects and will perform to any applicable specification published by us for 10 years from the date of purchase. Our liability under this guarantee is limited at our option to replacement of the product, repair of any damage to the immediate surface or area of application of the product, or compensation, in each case if we are satisfied loss or damage was due to a breach of this guarantee. This guarantee does not apply if damage or loss is due to failure to follow published instructions or any act or circumstance beyond our control, including shade variations and efflorescence. If you wish to make a claim under this guarantee you must notify us (Ardex Australia Pty Ltd, 2 Buda Way Kempas Creek NSW 2178; Toll Free: 1800 224 070; Email: technicalservices@ardexaustralia.com) and provide evidence of your purchase of the product within 30 days of any alleged loss or damage occurring. We reserve the right to ask you for satisfactory evidence of any alleged loss or damage. Any claim under this guarantee is at your cost. This guarantee is in addition to any rights or remedies you may have as a “consumer” under the Australian Consumer Law and to that extent you need to be aware that: “Our goods come with guarantees that cannot be excluded under the Australian Consumer Law. You are entitled to a replacement or refund for a major failure and for compensation for any other reasonably foreseeable loss or damage. You are also entitled to have the goods repaired or replaced if the goods fail to be of acceptable quality and the failure does not amount to a major failure”.

DISCLAIMER

The technical details, recommendations and other information contained in this data sheet are given in good faith and represent best of our knowledge and experience at the time of printing. It is your responsibility to ensure that our products are used and handled correctly and in accordance with any applicable Australian Standards. Our instructions and recommendations are only for the uses they are intended. Users are advised to confirm that this product is suitable for their application and conforms with the specifications of the system. We also reserve the right to update information without prior notice to you to reflect our ongoing research and development program. Country specific recommendations, depending on local standards, codes of practice building regulations or industry guidelines may affect specific installation recommendations. The supply of our products and services is also subject to certain terms, warranties and exclusions, which may have already been disclosed to you in prior dealings or are otherwise available to you on request. You should make yourself familiar with them.

© ARDEX Australia Pty Ltd 2025.

All aforementioned products are the trade marks of ARDEX Australia Pty Ltd, its licensors and affiliates.

This datasheet was issued in November 2025 and is valid for 3 years, in some instances a newer version may be published. Always refer to www.ardexaustralia.com for the latest technical data from ARDEX Australia Pty Ltd.