



ARDEX K275

Fast-Dry Commercial Floor Levelling Compound

Improved formula for faster application of floor coverings

2mm to 25mm in one application

Suitable for all commercial applications

ARDEX Australia Pty Ltd
2 Buda Way
Kemps Creek NSW 2178
Phone: 1300 788 780
Email: technicalservices@ardexaustralia.com
ardexaustralia.com

ARDEX New Zealand Ltd
15 Alfred Street, Onehunga Auckland,
New Zealand 1061
Phone: 0800 227 339
Email: info@ardexnz.com
ardex.co.nz

ARDEX K275

Fast-Dry Commercial Floor Levelling Compound

DESCRIPTION

ARDEX K275 is a levelling and smoothing compound with a new fast drying formula. It is designed to level and smooth internal sub-floors prior to applying floor finishes. It is a high-performance product, that is quick and easy to use, and provides a smooth level surface.

SUBSTRATES

ARDEX K275 is designed to be installed over internal concrete substrates as well as ARDEX A38, ARDEX A48 and ARDEX K900BF.

It is not recommended for use over timber, steel decking, or subfloors subject to vibration. For these areas, ARDEX recommends using ARDEX K 65 or ARDEX K 60 ArditeX. For more information on these types of applications, please contact ARDEX Technical Services.

SURFACE PREPARATION

Concrete floors must be solid, clean, and free of wax, grease, asphalt, latex compounds, curing and sealing compounds, and any other surface contaminants. To prepare the concrete floor, mechanically clean it using shot blasting, scarifying, diamond grinding, shaving, or other suitable methods to create a roughened, clean, sound, solid, and open porous surface.

Acid etching is not an acceptable method for cleaning the subfloor. Do not use solvents or sweeping compounds.

The subfloor must be dry (AS 1884) and primed properly for successful installation. The subfloor temperature must be at least 10°C. For more information, contact ARDEX Technical Services.

PRIMING

To prepare standard concrete floors for the installation of ARDEX levelling compounds, apply ARDEX P 51 primer. Mix 1 part ARDEX P 51 with 2 parts water and apply evenly with a bristle broom. Do not use paint rollers, mops, or spray equipment. Do not leave any bare spots. Brush off any puddles of excess primer. Allow the primer to dry to a thin, clear film for at least 3 hours and up to 24 hours.

For very absorbent concrete, two applications of primer may be required to avoid pinholes and bubbling in the levelling compound. In these cases, make the initial coat 1 part ARDEX P 51 diluted with 3 parts water. Allow the primer to dry and then apply a second coat of 1 part ARDEX P 51 diluted with 1 part water. Allow the primer to dry to a thin, clear film for at least 3 hours and up to 24 hours.

ARDEX Multiprime can be applied using a brush or roll covering the entire surface to be sealed. For very porous substrates, a second coat is required. Ardex multiprime must be dry prior to application of subsequent products. ARDEX Multiprime will dry in approximately 15-30 minutes at 25°C and 50% relative humidity.

DAMP OR GREEN CONCRETE

When a concrete substrate moisture content is measured at greater than 80% relative humidity (ASTM F2170) or exceeds 15gm/m²/24hrs (ASTM F1869) when tested in

accordance with AS 1884, an ARDEX Moisture barrier system should be used. This is typically equivalent to 5% or greater moisture content from a digital non-destructive moisture meter, however Australian Standards must be followed.

Option1 - Prime with ARDEX WPM300 and broadcast sand. Apply one coat of ARDEX WPM300 by roller at 3m²/litre. Whilst ARDEX WPM300 is still wet broadcast 0.5mm clean dry sand over the surface at ~700gms/m². Cure overnight and broom and vacuum excess sand off. Apply smoothing cement.

Option 2 - ARDEX WPM368 can be applied as a moisture barrier. Two coats are applied at 3m²/litre or WFT of 0.3mm per coat. A single coat of ARDEX WPM368 applied at 3m²/litre per coat acts as a moisture stop for 'green concrete' not subject to rising damp or permanent moisture. Broadcast sand is not required.

NON-POROUS SUBSTRATES

Option1 - Dilute ARDEX P9 single part primer with water 1:1 by volume and apply with a brush or roller with applications of leveller able to take place after approximately 20 minutes at 23°C and 50% relative humidity. Ensure ARDEX P9 single part primer is fully dry prior to the application leveller.

Option 2 - Using ARDEX P82 primer. Mix part A (red) with part B (white) and apply with a short-nap or sponge paint roller. Leave a thin, transparent pink coat of primer no heavier than a coat of paint. Do not leave any bare spots. Roll off any areas of excess primer. Allow the primer to dry to a thin, slightly tacky film for at least 3 hours and up to 24 hours.

Note: Low subfloor temperatures and/or high ambient humidity require longer drying times for ARDEX primers. Do not install levelling compounds until the primers have dried thoroughly.

MIXING RATIO

The mixing ratio for ARDEX K 275 is 4.5 litres of water to 20 kg of powder. When used in conjunction with ARDEX P 82 and for high stress areas, the mixing ratio changes to 1.25 litres of ARDEX E 25 with 3.75 litres of water per 20 kg bag of ARDEX K 275.

MIXING

ARDEX floor levelling products react and harden quickly when mixed with water. It is essential to mix the powder into the water thoroughly and quickly to ensure a lump-free mortar. The most efficient method of mixing is to use an ARDEX mixing paddle and a heavy duty electric drill (650rpm). The normal mixing time for a 20kg bag is 2 to 3 minutes. Concrete mixers and hand mixing are not suitable methods of mixing.

The mixing ratio of ARDEX K275 is 4.5 litres of water to 20kg of powder.

ARDEX K275

Fast-Dry Commercial Floor Levelling Compound

MANUAL INSTALLATION

After mixing ARDEX K 275, pour it onto the prepared subfloor and spread it using an ARDEX stand-up spreader or ARDEX hand trowel. Use an ARDEX gauging tool with height adjustment to achieve an even thickness. Use an ARDEX smoother for smoothing, feathering, and touch-ups. Do not rework ARDEX K 275 after 10 minutes. Wear football boots with rubber or nylon studs to avoid leaving marks in the liquid ARDEX K 275.

PUMPING INSTALLATION

For ease and efficiency of application ARDEX K275 can be pumped using an ARDEX approved mixing pump.

SPECIAL APPLICATIONS

ARDEX K 275 can be used over heated subfloors. For this application, mix ARDEX K 275 with 3.5 litres of water and 1.6 litres of ARDEX E 25 resilient emulsion. Contact ARDEX Technical Services for more information on these types of applications.

For areas subject to heavy traffic and heavy loads, such as supermarkets, longer curing times are required before the floor is subjected to highly loaded trolleys. At 23°C, it is recommended that 7 days of curing are allowed before heavy loads are applied. Lower temperatures may extend this time. ARDEX E 25 can also be used to increase the strength and resilience of the levelling compound.

THICKNESS

ARDEX K 275 can be applied in one coat in thicknesses from 2 mm to 25 mm without aggregate. For areas that require a thickness of more than 25 mm up to a maximum of 40 mm, ARDEX K 275 first must be mixed with well-washed and dried aggregate of 2-5 mm in size.

To do this, mix the ARDEX K 275 with water according to the mixing ratio, let it rest and then add the aggregate in equal volume to the mixed mortar while mixing.

COVERAGE

Approximately 1.7kg powder/mm/m². A 20kg bag will cover approximately 4m² at 3mm thickness.

DRYING-HARDENING

Drying time is dependent on jobsite temperature, humidity, installation thickness and floor covering type (Based on 23°C and 50% RH).

Walkable from 4 hours

Ready for tiles from 4 hours

Ready for floor coverings from 16 hours

Ready for direct stick timber flooring from 72 hrs

Always comply with floor covering manufacturer's moisture instructions. Higher temperatures will reduce the setting hardening and drying times, whilst lower temperatures will extend drying times.

SHELF LIFE

ARDEX K275 has a shelf life of 12 months when stored in the original unopened packaging, in a dry place at 23°C and 50% relative humidity.

TECHNICAL PROPERTIES	
Mixing Ratio	4.5L per 20kg Bag
Colour	Grey
Bulk Density of Powder	Approx 1.2kg/L
Coverage	4m ² at 3mm
Weight of Fresh Mortar	2.0kg/L

COMPRESSIVE STRENGTH	
After 1 day	Approx 17 MPa
After 7 days	Approx 25 MPa
After 28 days	Approx 40+ MPa

FLEXURAL STRENGTH	
After 1 day	Approx 4 MPa
After 7 days	Approx 8 MPa
After 28 days	Approx 10 MPa

PACKAGING

ARDEX K275 is packed into 20kg polylined paper bag

SAFETY DATA

This product causes skin irritation and may cause an allergic skin reaction. It may cause respiratory irritation and causes serious eye damage. This product is suspected of causing genetic defects and causes damage to organs through prolonged or repeated exposure. In case of contact with the eyes rinse with running water until advised to stop by the Poisons Information Centre or a doctor, or for at least 15 minutes. Wear protective gloves, clothing, eye, and face protection. Avoid inhaling dust/fumes. Ensure adequate ventilation during mixing and application. Store locked up. Check with your local Council regarding the disposal of contents, dispose of packaging thoughtfully and recycle where possible. Keep out of the reach of children. Call the Poisons Information Centre on 131 126 (AUS) and 0800 764 766 (NZ) or call a doctor if you feel unwell. Additional information is in the Safety Data Sheet (SDS) at ardexaustralia.com or ardex.co.nz

ARDEX K275

Fast-Dry Commercial Floor Levelling Compound

GUARANTEE

ARDEX Australia Pty Ltd (“we” or “us”) guarantees this product (“our goods”) is free from manufacturing defects and will perform to any applicable specification published by us for 10 years from the date of purchase. Our liability under this guarantee is limited at our option to replacement of the product, repair of any damage to the immediate surface or area of application of the product, or compensation, in each case if we are satisfied loss or damage was due to a breach of this guarantee. This guarantee does not apply if damage or loss is due to failure to follow published instructions or any act or circumstance beyond our control, including shade variations and efflorescence. If you wish to make a claim under this guarantee you must notify us (ARDEX Australia Pty Ltd, 2 Buda Way NSW 2178; Toll Free: 1800 224 070; Email: technicalservices@ardexaustralia.com) and provide evidence of your purchase of the product within 30 days of any alleged loss or damage occurring. We reserve the right to ask you for satisfactory evidence of any alleged loss or damage. Any claim under this guarantee is at your cost. This guarantee is in addition to any rights or remedies you may have as a “consumer” under the Australian Consumer Law and to that extent you need to be aware that: “Our goods come with guarantees that cannot be excluded under the Australian Consumer Law. You are entitled to a replacement or refund for a major failure and for compensation for any other reasonably foreseeable loss of damage. You are also entitled to have the goods repaired or replaced if the goods fail to be of acceptable quality and the failure does not amount to a major failure”.

DISCLAIMER

The technical details, recommendations and other information contained in this data sheet are given in good faith and represent the best of our knowledge and experience at the time of printing. It is your responsibility to ensure our products are used and handled correctly and in accordance with any applicable Australian Standards. Our instructions and recommendations are only for the uses they are intended. We also reserve the right to update information without prior notice to you to reflect our ongoing research and development program. Country specific recommendations, depending on local standards, codes of practice, building regulations or industry guidelines, may affect specific installation recommendations. The supply of our products and services is also subject to certain terms, warranties and exclusions, which may have already been disclosed to you in prior dealings or are otherwise available to you on request. You should make yourself familiar with them.

© ARDEX Australia Pty Ltd 2026.

All forementioned products are the trade marks of ARDEX Australia Pty Ltd, it's licensors and affiliates.

This data sheet was issued in January 2026 and is valid for 3 years, in some instances a newer version may be published. Always refer to www.ardexaustralia.com for the latest technical data from ARDEX Australia Pty Ltd